



PANDA ANTICORROSIVE SYNTHETIC PAINT

DESCRIPTION: Alkyd based anticorrosive primer

SPECIFICATIONS: Used as anti-corrosive primer on all metal surfaces in interior and exterior places. Forms a solid base for synthetic paints. Primer for metal surfaces with good adhesion and coating ability.

Technical details:

Solid content % (by weight) :

76+78

Density (g/cm³ ,20°C):1.50-1.60

Viscosity (KU,25°C) : 120+5

Solidification point: > 38 °C

APPLICATION: Surfaces must be cleaned and sanded from dirt, rust and old paint bubbles. It is applied in two layers. You must wait 1 day before applying the second layer. Can be thinned by 10-15% with Panda SYNTHETIC SOLVENT. Applied by brush, roller or spray, at a temperature from + 5 ° C to + 30 ° C. Clean the tools you use with Panda Synthetic Solvent immediately after application.

DRYING TIME: Touch dry in 2-3 hours, dust-free dry in 5-6 hours, hard dry in 12-15 hours.

COVERAGE AREA: 15 m² /L when applied in a single layer.

SHELF LIFE: It can be stored in a closed container in a cool and dry place, protected from frost and direct sunlight . For safe storage of the paint remaining in the container after use, thinner should be added until the paint is completely covered, or the container should be closed tightly and turned 180 ° once or twice.

SAFETY PRECAUTIONS: R10 : Flammable. R20/21/22: Harmful in contact with skin and if inhaled or swallowed.

S2: Keep out of reach of children. S16: Keep away from sources of ignition. NO SMOKING

S24/25: Avoid contact with eyes and skin. S46: If swallowed consult a doctor immediately; show the container or the label; S51: Use only in well-ventilated areas.

- Certified with AZS-034-98
- Certified with ISO 9001:2008

Panda Boya: Binagadi Highway, 4th Madan str.276/1

Tel:(+994 12) 401 90 00, Fax:(+994 12) 448 16 19